



## TECHNICAL DATA SHEET

### Multicor LF 30

Mineral oil-containing anti-corrosion oil, low viscosity, with hand sweat neutralising additives

#### PRODUCT DESCRIPTION

- + solvent-free anti-corrosion oil
- + on the basis of mineral oil
- + contains hand sweat neutralising additives
- + mild odour

#### CHARACTERISTICS

Colour / DIN ISO 2049 lighter 3.5

---

Density/15°C / DIN EN ISO 12185 880 kg/m<sup>3</sup>

---

Viscosity/20°C / ASTM D 7042 30 mm<sup>2</sup>/s

---

Flash point (Cleveland) / DIN ISO 2592 > 150 °C

---

Type of protective film oily

---

Film thickness after dipping 3 - 4 µ

---

Kesternich test / DIN EN ISO 6270-2 25 cycles

---

Salt spray test / DIN EN ISO 9227 20 hour(s)

#### APPROVAL

Multicor LF 30 fulfils the Bosch negative list concerning aromatic containing substances.

81470

10/2020-81470-7

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can not be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.



## TECHNICAL DATA SHEET

### **Multicor LF 30**

Mineral oil-containing anti-corrosion oil, low viscosity, with hand sweat neutralising additives

#### **APPLICATION**

**Multicor LF 30** is used for preservation of inner and outer surfaces of semi-finished parts, machine elements, replacement parts, tools and such things when being stored in protected rooms.

The product is applied in as-delivered condition by dipping, spraying or manually e.g. by brush.

#### **DEGREASING**

We recommend degreasing with aqueous-alkaline as well as solvent cleaners.

#### **NOTE / ATTENTION**

The specifications of the film thickness are only guiding values which are highly dependent on the surface texture and the type of applications.

Benefit from our service, we will gladly advise you and develop individual application recommendations for your process. Please also note the material safety data sheet.

81470

10/2020-81470-7

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can not be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.

2 / 2